

## System I

Under water area ( after surface preparation )  
1 comp. products

**v.Höveling YACHTFARBEN**



Pos.No.	Paint	Mixing ratio by weight	Theoretical coverage approx. m <sup>2</sup> / l	Application	Application surface temperature	Drying time at 15°C, 80% rel.humidity		Overcoating intervall		Thinner / Cleaner for goods	Recommended number of coatings for boat building-material and special materials on bord			
						dustfree	resistant against rain	min.h.	max.days		glassfibre, reinforced plastic	wood not teak	steel	stainless steel sea-water resitant aluminium non-ferrous metals
1	D 50 Antorit Zinkgrund	15+1	12	B/R/AS	10-30	4	12	24	90	990			1	
2	D 80 Universalgrund 6055		7	B/R/AS/LS	5-30	1	2	3	90	799		4 - 5 *	5 -6*	5 -6*
3	type acc. to area of journey see table of antifouling											2	2	2

\* With airless spraying the doable film thickness is possible.Then only 2-3 are necessary