

System III

Above water line , coloured (after surface preparation)
1 comp. products



Pos.No.	Paint	Mixing ratio by weight	Theoretical coverage approx. m ² / l	Application	Application surface temperature	Drying time at 15°C, 80% rel.humidity		Overcoating intervall		Thinner / Cleaner for goods	Recommended number of coatings for boat building-material and special materials on bord			
						dustfree	resistant against rain	min.h.	max.days		glassfibre, reinforced plastic	wood not teak	steel	stainless steel sea-water resitant aluminium non-ferrous metals
1	D 50 Antorit Zinkgrund	15+1	12	B/R/AS	10-30	4	12	24	90	990			1	
1a	D 53 Antorit Epoxi-Primer	10+1	13,7	P/R/AS/LS	10-30	1	12	3	180	809				1
2	D 80 Universalgrund 6055		11,5	B/R/AS/LS	5-30	1	2	3	90	799		2-3	2	1
3	D 10 Super Yacht Vorlack		12	B/R/AS/LS	5-30	2	8	8	90	799	(1) *	1	1	1
4	D 01 Super Yachtlack 2000		12	B/R/AS/LS	10-30	3	18	24	90	799	(2) *	2	2	2

* only if no 2 comp.product is wished