

## System VI

Wood inside , clear satin-matt ( after surface preparation )

**v.Höveling YACHTFARBEN**



Pos.No.	Paint	Mixing ratio by weight	Theoretical coverage approx. m <sup>2</sup> / l	Application	Application surface temperature	Drying time at 15 °C, 80% rel.humidity		Overcoating intervall		Thinner / Cleaner for goods	Recommended number of coatings for boat building-material and special materials on board			
						dustfree	resistant against rain	min.h.	max.days		glassfibre, reinforced plastic	wood not teak	steel	stainless steel sea-water resitant aluminium non-ferrous metals
1	D 03 Yacht Klarlack 2585 *		15	B/LS	10-30	4	8	24	90	799	5	5		5
1a	alternative to 1: D 83 DD-Hartlack glossy *	2+1	10	B/LS	10-30	1	4	8	2	008	5	5	5	5
1b	alternative to 1 D 12 Aqua-Kajüt-Klarlack ** satin-matt		10	B/LS	10-30	2	24	24	30	Water	2-3	2-3	2-3	2-3

\* 1st coat with 30% - 40% added thinner

\* 2nd coat with 10% -20% added thinner

After the first coat the upright standing gravis are sanded.

\*\* Aqua Kajüt-Klarlack should be applied without additional thinner